















龙牌

# 分散染料

Dragonperse Dyes





















寧波保稅區洪大化工實業有限公司  
NINGBO FREE TRADE ZONE HONGDA CHEMICAL INDUSTRIAL CO.,LTD

	龙牌分散染料 DRAGONPERSE		染色深度 Dyeing depth owf %	色牢度 Fastness			pH 范围 pH range
	色样 Color Sample (涤纶) (Polyester)	染料名称 Name of Dyes		耐光 (氙灯) Light (Xenon)	耐洗 Washing 60°C	耐干热 (升华) Sublimation 180°C	
UN-SE、AC-E 超细纤维及快速染色系列 AC-E、UN-SE series for Rapid dyeing and Microfiber		黄 AC-E 100% Yellow AC-E	0.5	6	4	3-4	4~10
		红 AC-E 100% Red AC-E	0.5	7	4	3-4	4~10
		蓝 AC-E 100% Blue AC-E	0.5	7	4	3-4	4~10
		黄 UN-SE 200% Yellow UN-SE	1.0	6	4	4-5	3~8
		橙 UN-SE 200% Orange UN-SE	1.0	6	4	4	3~8
		红 UN-SE 200% Red UN-SE	2.0	5	3-4	3-4	3~8
		红玉 UN-SE 200% Rubine UN-SE	1.5	5	4	3-4	3~8
		蓝 UN-SE 200% Blue UN-SE	2.0	5	4	3-4	3~8
		深蓝 UN-SE 200% Navy UN-SE	3.0	6	3-4	4	4~7
	CXF 系列高坚牢度分散染料 CXF series Disperse Dyes for high fastness		黄 CXF-6G 200% Yellow CXF-6G	1.5	6	5	5
		橙 CXF-2G 200% Orange CXF-2G	1.0	6	4-5	4-5	4~9
		红 CXF-2G 200% Red CXF-2G	1.0	5-6	4-5	4-5	3~9
		艳红 CXF-B 200% Brill.Red CXF-B	0.5	5-6	4	4	4~9
		红 CXF-KB 200% Red CXF-KB	2.2	5-6	4-5	5	3~9
		红 CXF-4BN 200% Red CXF-4BN	1.0	6	4-5	4-5	3~9
		蓝 CXF-G 200% Blue CXF-G	2.0	7	4-5	4-5	4~9
		深蓝 CXF-R 200% Navy CXF-R	2.0	6	4	4-5	4~7
		黑 CXF-R 200% Black CXF-R	4.0	6	4	4-5	4~7

龙牌分散染料 DRAGONPERSE		染色深度 Dyeing depth owf %	染料索引 C.I. Disperse No.	色牢度 Fastness				
				耐光(氙灯) Light (Xenon)	耐洗 Washing 60°C	耐干热升华 (180°C) Sublimation	耐汗渍 Perspiration	耐摩擦(干湿) Rubbing (wet, Dry)
染料名称 Name of Dyes	色样 Color Sample (涤纶) (Polyester)							
荧光黄 8GFF Fluor.Yellow 8GFF 100%		2.0	Y   82	4	4-5	5	4	4 4
荧光黄 II Fluor.Yellow II 100%		2.0	Y   71	6-7	4-5	4-5	4	4-5 4-5
艳黄 SE-6GLN Brill.Yellow SE-6GLN 100%		1.1	Y   49	7	4	4-5	4	4 4
艳黄 6GSL Brill.Yellow 6GSL 200%		1.0	Y   114	7-8	4-5	4-5	4-5	4-5 4-5
艳黄 C-SG Brill.Yellow C-SG 200%		0.8	Y   119	6-7	5	5	5	5 5
艳黄 SE-4GL Brill.Yellow SE-4GL 300%		0.8	Y   119: 1	6	4-5	4	4	4-5 4-5
黄 5GL Yellow 5GL 200%		1.3	Y   241	6-7	5	4-5	5	5 4-5
艳黄 C-4G Brill.Yellow C-4G 200%		0.8	Y   211	7	4	3-4	5	5 5
黄 S-G Yellow S-G 100%		1.0	Y   79	7	4-5	5	5	4-5 4-5
黄 G Yellow G 100%		1.6	Y   3	6	4-5	3	5	4 4
黄 SE-FL Yellow SE-FL 100%		3.5	Y   42	6-7	5	4-5	5	4-5 4-5
黄 3GE Yellow 3GE 200%		1.2	Y   54	6	4	4	4-5	4-5 4
黄 E-3G Yellow E-3G 200%		1.5	Y   64	6-7	4-5	4-5	5	5 4-5
黄 RGFL Yellow RGFL 100%		1.9	Y   23	7	4	4	5	4-5 4-5
黄 SE-RL Yellow SE-RL 300%		1.0	Y   23: 1	6	4-5	4-5	4-5	4 4
金黄 GG Golden Yellow GG 100%		2.0	Y   56	6-7	5	5	5	4-5 4-5
橙 R-SF Orange R-SF 200%		0.8	O   73	5-6	5	5	5	4-5 4-5
黄棕 S-2RFL Yellow Brown S-2RFL 100%		1.65	O   30	5-6	4	4-5	4-5	4-5 4-5

龙牌分散染料 DRAGONPERSE			染色深度 Dyeing depth owf %	染料索引 C.I. Disperse No.	色牢度 Fastness				
染料名称 Name of Dyes	色样 Color Sample (涤纶) (Polyester)	耐光(氙灯) Light (Xenon)			耐洗 Washing 60°C	耐干热(升华) Sublimation 180°C	耐汗渍 Perspiration	耐摩擦(干湿) Rubbing (wet, Dry)	
橙 S-3GL Orange S-3GL	200%		1.1	O   29	5	4-5	4	4-5	4 3-4
橙 2R Orange 2R	200%		0.6	O   25	6	5	5	5	4-5 5
橙 S-3RFL Orange S-3RFL	200%		0.8	O   44	6-7	4-5	3-4	4-5	4-5 4-5
橙 REL Orange REL	200%		1.0	O   61	6-7	4-5	4	4-5	4-5 4
橙 SE-2RL Orange SE-2RL	200%		0.85	O   78	6	5	4	4-5	4-5 4-5
橙 B-2R Orange B-2R	200%		0.8	O   76	7	4-5	4	4-5	4 4
大红 S-3GFL Scarlet S-3GFL	100%		1.6	R   54	5-6	3-4	4-5	4	4-5 4
大红 B Scarlet B	200%		1.0	R   1	4-5	3-4	3	5	3 3
大红 S-BWFL Scarlet S-BWFL	100%		1.8	R   74	6-7	4-5	4-5	4	3 4-5
红 GS Red GS	200%		1.3	R   153	3	4	4-5	4-5	4-5 4-5
大红 BRE Scarlet BRE	100%		2.0	R   135	6	4	5	4-5	4-5 4-5
红 E-R Red E-R	200%		1.2	R   50	6-7	5	4-5	5	4-5 5
红 BS Red BS	200%		1.4	R   152	5-6	3-4	5	4-5	4-5 4-5
荧光红 2GL Fluor.Red 2GL	100%		2.0	R   277	4	3-4	4	4	3 3
荧光桃红 BG Flour.Pink BG	100%		2.0	R   196	4	4	4	-	3 3-4
桃红 R3L Pink R3L	200%		2.0	R   86	7	4	5	4	4 4-5
艳桃红 REL Brill.Pink REL	150%		3.0	R   91	6-7	4-5	3-4	4-5	4 4-5
红 FB Red FB	200%		1.2	R   60	6	4-5	4-5	4-5	4-5 4-5

龙牌分散染料 DRAGONPERSE			染色深度 Dyeing depth owf %	染料索引 C.I. Disperse No.	色牢度 Fastness				
染料名称 Name of Dyes	色样 Color Sample (涤纶) (Polyester)	耐光(氙灯) Light (Xenon)			耐洗 Washing 60°C	耐干热(升华) Sublimation 180°C	耐汗渍 Perspiration	耐摩擦(湿干) Rubbing (wet, Dry)	
红 FBL Red FBL	200%		2.4	R   92	5-6	4-5	4-5	4-5	4-5 4-5
红 F3BS Red F3BS	100%		1.4	R   343	4-5	4-5	4-5	4	3 3
红 FRL Red FRL	100%		2.0	R   177	5-6	5	4	4-5	5 5
红玉 S-2GFL Rubine S-2GFL	100%		1.3	R   167	5-6	4-5	4-5	4	4-5 4-5
红玉 SE-GFL Rubine SE-GFL	200%		0.8	R   73	5-6	4-5	4-5	4-5	4-5 4-5
红玉 BBL Rubine BBL	200%		1.0	R   82	6	4-5	4	4-5	4 4-5
红 2B Red 2B	200%		1.0	R   13	4-5	3-4	3	4-5	3 3
红 RBF Red RBF	200%		1.0	R   179	6-7	3-4	5	4-5	4-5 4-5
紫 C-B Violet C-B	200%		1.2	V   33	6-7	4-5	4	5	4-5 4-5
红 PG Red PG	200%		1.1	R   311	6	5	5	-	4-5 4-5
紫 HFRL Violet HFRL	150%		1.5	V   26/31	5-6	4-5	4-5	4-5	4 4-5
紫 S-4RL Violet S-4RL	200%		1.0	V   77	6-7	5	5	5	5 5
紫 2R Violet 2R	100%		2.5	V   1	3-4	4-5	4-5	4-5	4 4
紫 S-3RL Violet S-3RL	200%		0.6	V   63	5-6	4-5	4-5	5	4-5 5
紫 RL Violet RL	200%		1.5	V   28	5-6	4-5	4-5	4-5	5 5
紫 SE-5R Violet SE-5R	200%		0.5	V   93:1	4-5	3-4	4	4-5	4 4
蓝 RD Blue RD	200%		3.0	B   106	5	4	4	4-5	4-5 4-5
蓝 3RT Blue 3RT	200%		1.0	B   148	5	5	4-5	4-5	4-5 4-5

龙牌分散染料 DRAGONPERSE			染色深度 Dyeing depth owf %	染料索引 C.I. Disperse No.	色牢度 Fastness				
染料名称 Name of Dyes	色样 Color Sample (涤纶) (Polyester)	耐光(氙灯) Light (Xenon)			耐洗 Washing 60°C	耐干热(升华) Sublimation 180°C	耐汗渍 Perspiration	耐摩擦(十湿) Rubbing (wet, Dry)	
蓝 S-3RF Blue S-3RF	100%		2.0	R   257	6-7	5	5	4-5	4-5 5
蓝 CR-F Blue CR-F	200%		0.8	B   366	5	4	4	4-5	4-5 5
蓝 SE-2R Blue SE-2R	100%		1.0	B   183:1	5-6	4-5	4-5	4-5	4-5 4-5
蓝 C-R Blue C-R	200%		3.0	B   284	3	5	4-5	4-5	4-5 4-5
蓝 S-BGL Blue S-BGL	200%		1.0	B   73	6	4-5	4-5	4-5	4-5 4-5
蓝 BBLS Blue BBLS	200%		2.0	B   165	6-7	4-5	5	5	5 5
蓝 2BLN Blue 2BLN	150%		1.5	B   56	6	4-5	4-5	4-5	4-5 5
蓝 2BL Blue 2BL	300%		0.4	-	4	4	3-4	4-5	4-5 4-5
蓝 FFR Blue FFR	100%		2.5	B   3	5-6	4	5	4-5	4-5 4-5
深蓝 HGL Navy Blue HGL	150% 200%		1.0	B   79	5	4	4-5	5	4 4
蓝 AR Blue AR	200%		1.0	B   281	5	4-5	4-5	4-5	4-5 4-5
蓝 5GR Blue 5GR	300%		0.6	B   291:1	6-7	4-5	4-5	5	5 5
蓝 5G Blue 5G	300%		0.6	B   291	6-7	5	4-5	5	5 5
蓝 F2GS Blue F2GS	200%		1.1	B   367	5	4	4-5	4-5	4-5 4-5
蓝 SBGL Blue SBGL	200%		3.0	B   87	7	4-5	4-5	4-5	4-5 4-5
翠蓝 HGL Turq. Blue HGL	200%		3.5	B   60	7-8	4-5	5	5	5 5
翠蓝 BFS Turq. Blue BFS	200%		2.0	B   143	7	4-5	4-5	4-5	4-5 4-5
绿 C-6B Green C-6B	100%		3.0	G   9	4-5	5	5	5	5 5

